



TECA-PRINT-PRODUCT INFORMATION

UV-PAD PRINTING INKS METAL EFFECT INK TONES NOW AVAILABLE

The metal effect ink tones with the article descriptions 75, 76, 77, 78 and 79 are now also available for the UV-pad printing inks 760, TPC 770, TPC 780, TPC 790 and TPC 860.

The three well-known golden ink tones as well as one silver and one copper ink tone so also can be used when you work with UV-inks.

In contrary to all ink tones available until now, these metal effect ink tones are not ready to print when they are delivered. The mixing of these ink tones, which happens with the lack GF-13, has to be done directly before using them.

Reason: The metal pigments of the gold and silver metal ink tones can react with the pH-sour UV-parts. This means that metal effect ink tones have to be used directly after having mixed them (latest within approximately 24 hours).

The metal bronze paste 75, 76, 77, 78 and 79 are supplied only in 1 litre tins. The lack GF-13 has to be ordered separately according to the used ink type. The mixing of the metal effect ink and the lack has to be done before printing. For the mixing, the following relations are valid:

Gold bronze paste : Lack GF-13	=	1 : 3
Silver bronze paste : Lack GF-13	=	1 : 4

Please find further information about the UV-metal effect ink tones on the technical information sheets of the corresponding ink type.